



AKFIX POLYUREA PA 1070

1 – PRODUCT DESCRIPTION

Akfix polyurea PA 1070 is a two component, rapid curing, UV resistant, 100% color stable new generation polyaspartic based polyurea surface coating system for both decorative and protective applications. On account of the UV and color fast properties, it is ideal for use as thin layer coating and clear topcoat sealer for surface protection on existing coating systems. After the product is completely cured, it forms a glossy, smooth top layer with high scratch, abrasion and chemical resistance. Polyaspartic system can be applied in a single or multiple coats by roll, brush or squeegee to a variety of substrates including concrete and metal.

2 – FEATURES

- Excellent UV light resistance
- Long working and gel time
- Fast reactivity and cure time (applicable to pedestrian traffic after 3-4 hours)
- Rapid return to service (return to service in 24 hours)
- Easy application and spreading
- Excellent adhesion to concrete and metal substrates
- High abrasion, impact and corrosion resistance
- Excellent chemical resistance
- Resistant to chlorine and saltwater
- High hydrolysis resistance
- Perfect thermal stability
- Available in transparent and several RAL colours

3– APPLICATION AREAS

- As top layer over polyurea coatings where UV resistance and color stability is required
- Clear sealer over decorative concrete surfaces
- Swimming pools, terraces and garage floors
- Restaurant and hospital flooring
- Water parks, amusement parks and decorative applications

4 – SURFACE PREPARATION & APPLICATION

Surface Preparation: Polyaspartic coating adheres perfectly to dry and clean metal and concrete surfaces. Concrete substrates must be prepared mechanically using abrasive blast cleaning to remove cement laitance and achieve an open textured surface. Weak concrete must be removed and surface defects such as voids must be fully exposed. Repairs to the substrate, filling of voids and surface levelling must be carried out using appropriate products. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum. The substrate should be dry to 85% RH and free from rising damp and ground water pressure. Concrete moisture content can vary widely depending on work-site conditions. Sealing wet or humid concrete can lead to blistering and/or delamination of coating. Relative air humidity for application should be lower than 85%. Be aware of condensation; the substrate must be at least 5°F (3°C) above dew point to reduce the risk of condensation of the coating. Prior to application, confirm substrate moisture content, relative air humidity and dew point. The application surface has to be primed in order to achieve an even surface and good adhesion.



TECHNICAL DATA SHEET

Akfix® coating

Yeşilbayır Mah. Şimşir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

www.akfixcoating.com - info@akfixcoating.com

After the primer is cured, apply the product. For metal substrates sandblasting and priming is recommended for best performance.

Mixing: Before using the both components have to be stirred well separately and then component B has to be poured into component A completely and then the combined products must be mixed thoroughly with a paddle mixer on slow speed for two minutes until a homogenous liquid achieved. Stir gently, avoid over mixing or creating a vortex that would introduce air. After mixing the product should be rested for 2-3 minutes. Do not mix below the dew point, which will shorten the pot life. Do not apply in direct sunlight when temperatures and humidity are high.

Application: The product can be applied by roller, brush or squeegee. Roller application is the recommended process. Ideally the roller should be an industrial grade phenolic resin core with a synthetic nap. Small chip brushes may be used along the perimeter and in more difficult to reach areas. Maximum application thickness in a single application is 0,25 mm. Material will be dry to the touch 1-2 hours after application, dependent on ambient temperature, slab temperature and humidity. When applying two coats the first coat must be tack free before applying the second coat and the product may be recoated within 2-24 hours following application. The times specified can only be used as guidelines. The exact times have to be determined by testing on site. All application equipment must be cleaned with acetone, MEK, MIBK and xylene like solvents.

Nonskid Finish: Polyurea PA 1070 can be used to produce a durable nonskid finish with different textures. The desired nonskid additive should be added to the resin component and thoroughly blended prior to mixing with the iso component. Apply at a maximum wet film thickness of 0,15 mm for best results. If wet film thickness is too high the nonskid effect will be lost and surface appearance will not be uniform. If higher film build is required apply multiple thin coats for best performance and uniform appearance. Optionally, the non-skid coat can be applied as the final coat only.

5- PACKAGING

- 10 kg set;
- 4 kg bucket (Amine side)
- 6 kg bucket (Isocyanate side)

6- SHELF LIFE & STORAGE CONDITIONS

Polyurea components are sensitive to moisture. Keep polyurea components in tightly closed containers. Store the polyurea components between 20 -30 °C. It has nine months of storage time, if stored according to stated conditions.

7- SAFETY

Avoid breathing vapors. Avoid contact with skin and eyes. Take precautions during application. Wear suitable protective clothing, gloves and eye/ face protection. Adequate ventilation of the working area is recommended. Refer to SDS sheet prior to use.



TECHNICAL DATA SHEET

Akfix® coating

Yeşilbayır Mah. Şimşir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

www.akfixcoating.com - info@akfixcoating.com

8- TECHNICAL FEATURES

Component Properties

	UNIT	METHOD	AMINE COMPONENT (A)	ISO COMPONENT (B)
Density (25°C)	gr/cm ³	ASTM D 1217	1,07-1,1	1,12-1,15
Viscosity (25°C)	mPa.s	ASTM D 4878	1000-1100	6000-7000
Shelf life	-----	-----	6 months	6 months

Physical Properties

	METHOD	DATAS
Chemical structure		A: Amine Resin B:HDI Prepolymer
Mix ratio (by weight)	--	40:60 (A:B)
Consumption (g/m ²)	--	150-200
Recommended thickness (µm)	--	150-200
VOC content (%)	ASTM D1259	0
Solid content (%)	ASTM D2697	95
Gel time (min)	--	30-35*
Tack free time (min)	--	60-70*
Pedestrian traffic time (hr)	--	3-4*
Full cure time (day)	--	7*
Tensile strength (MPa)	ASTM D638	> 9
Elongation at break (%)	ASTM D638	>100
Hardness (Shore A)	ASTM D2240	65-70

*Drying time is temperature, humidity and film thickness dependent. Thicker films will take longer to through-cure. High humidity will shorten cure time Properties were tested at 25°C 50% R.H.

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.