

SPR 235

Closed Cell, Rigid Spray Polyurethane Foam

1 - Description

SPR 235 PU system is designed for spray application of polyurethane foam. The material must be applied with a high pressure plural component spray polyurethane machine. Resulting foam has excellent physical properties and is classified according to DIN4102 B2 norm. The foam stability and adhesion to the application surface is excellent. Reaction profiles suitable for over the floor, on wall and under the ceiling.

SPR 235 contains ecological low GWP blowing agents that do not damage the ozone layer.

2 - Product Information

Packacking	470 kg set (250kg PMDI) + (220kg Polyol Blend)
Shelf Life	6 months
Storage Conditions	Store in cool and dry conditions between +10°C to +30°C (+50°F to +86°F)

3 - Properties

- Two component
- Closed cell structure
- B2 (E) fire reaction
- Easy and high application speed (~ 1000 m² per day)
- Seamless, no heat bridge
- Self-adhesive properties on many surfaces (concrete, wood, metal etc.)
- Does not grow insect and fungus
- Excellent thermal insulation for a long time (70-80 years)
- High energy saving
- Water vapor permeability
- Excellent mechanical properties
- Low storage and transportation cost
- Partial sound insulation

4 - Application Areas

- Roof
- Floor
- Wall
- Ceiling
- Chicken farms and barns
- Ships and storage tanks
- Cold storage room
- Other thermal insulation areas

5- Technical Data

	Method / Conditions	Polyol Blend	Polymeric MDI
Physical Appearance	--	Liquid	Liquid
Density	ASTM D 891 / 20°C	1,14 ±0,01 gr/ml	1,23 gr/ml
Viscosity	ASTM D 4878 / 25°C	250-350 cps	220-250 cps
NCO Content	ASTM D 5155	-	30-31 %
OH Content	ASTM D 4274	290-310 mgKOH/g	-

Reaction Parameters	Unit	Data
Cream Time	sec.	2-3
Gel Time	sec.	7-9
Tack Free Time	sec.	10-11
Free Rise Density	kg/m ³	35±1

* Tests were performed at 15°C (59°F) under laboratory conditions.

Finished Product Features:

Test Name	Unit	Method	Data
Application Core Density	kg/m ³	--	> 40
Closed Cell Content	%	EN 4590	≥ 90
Fire Reaction	--	EN 13501	E
		DIN 4102	B2
Service Temperature	°C	-	(-30) – (100)
	°F	-	(-22) – (212)
Water Absorption Amount	kg/m ²	EN 1609	0,20 (Declared)
			<0,20 (Measured)
Thermal Conductivity Coefficient	(W/m.K)	EN 12667	0,021
Thermal Conductivity Coefficient of Aging	(W/m.K)	EN 14315	0,028 (Declared)
			~0,027 (Measured)
Compressive Strength	kPa	EN 826	300~ 310

6 - Performance Chart

e _p	20	30	40	50	60	70	80	90	100	110
λ _M	0,026	0,026	0,026	0,026	0,026	0,026	0,026	0,026	0,026	0,026
R	0,78	1,16	1,55	1,94	2,33	2,72	3,10	3,49	3,88	4,26
e _p	120	130	140	150	160	170	180	190	200	
λ _M	0,026	0,026	0,026	0,026	0,026	0,026	0,026	0,026	0,026	
R	4,65	5,04	5,43	5,81	6,2	6,59	6,98	7,36	7,75	

e_p: Thickness; (mm)

λ_M: Average measured aged thermal conductivity; (W/mK)

R: Thermal resistance level; (m² K/W)

7 - Application Conditions

- The application surface should be clean and dry, the elements that prevent adhesion should be cleaned from the surface. Do not wash to clean the surface.
- Recommended temperature of application surface is between 5°C and 40°C (41°F and 104°F).
- The recommended air temperature is between 10°C and 40°C (50°F and 104°F).
- It is not recommended to apply in windy weather.
- Recommended component temperatures and machine settings are as follows.

Parameters	Data	
Polyol Blend Temperature	40-55°C	104-130°F
Polymeric MDI Temperature	40-55°C	104-130°F
Hose Temperature	35-55°C	104-130°F
Machine Pressure	80-110 bar	1160-1600 Psi

* Settings may vary depending on weather conditions and machine specifications.

- In order to obtain mixture in the right ratio, the filters of the machine should be cleaned and pump maintenance should be done. Improper mixing ratio of components results in low quality foam formation. In addition, the improper mixing ratio causes the adhesion problem, the increase in consumption, the deterioration of the cell structure and the foam not reaching the desired hardness.

Mixing Ratio	Unit	Data
Polyol Blend / Polymeric MDI	By volume	100 / 100
	By weight	100 / 110

8 - Directions for Use

- AKFIX SPR 235 is applied in layers to the surface to be thermal insulation until the desired thickness is obtained. Application is made in different thicknesses according to the regional climate conditions and application areas.
- The ideal application thickness for each layer is between 1.0 cm and- 2.0 cm. If thicker than 2.0 cm is applied, blistering may occur due to exothermic reaction.
- Since the surface is generally cold in the first layer application, the reaction is slow and the desired thickness cannot be obtained. Therefore, the first coat application is usually applied as a primer layer. In the second layer application to be applied, the desired thickness will be obtained more easily because the surface is warmer.
- In outdoor applications which is under direct sunlight, the foam color becomes darker after a period of time, the foam surface becomes dusty and the foam becomes more brittle. Polyurea (AKFIX POLYUREA Series), liquid PU membrane (AKFIX PU MEMBRANE Series) or acrylic membrane (AKFIX EM600) must be applied to protect the foam from UV rays.

9 - Consumption

- Material consumption may vary for many reasons. These reasons are the air temperature, application surface temperature, machine temperature settings, mixing ratio, number of application layers and so on.
- According to the application thickness and the number of application layers the theoretical consumption table is as follows.

Application Thickness	Consumption (kg)
3 cm	1,80 – 2,10
5 cm	2,80 – 3,20
10 cm	5,30 – 5,80

* The applied layer thickness is between 1,00 cm - 1,50 cm.

Rev no:0005 Rev Date: 24.07.2023

10 - Remarks & Restrictions

- AKFIX SPR 235 components are moisture sensitive. For this reason, it should be stored in original, unopened and undamaged packages, in store which is dry and not under direct sunlight.
- Storage of the components at low temperature can lead to increased viscosities of the components resulting in difficulty in application and crystallization of polymeric MDI.
- Storage of the components at high temperature causes evaporation of the blowing agent in polyol mixture and swelling of the barrel. In addition, when the pump is placed in the drum, it causes the material to bubble uncontrollably.
- The lids of the completely non-consumed drums should be closed tightly to prevent air entrance to barrel.
- Clean all tools and application equipment with suitable cleaner solvent immediately after use. Hardened and cured material can only be cleaned by mechanical methods.
- Read the MSDS form carefully before using the AKFIX SPR 235 product or when a problem is encountered and follow the written instructions.
- Personal protective equipment and full face mask with appropriate filter should be used during application.
- There must be sufficient air circulation in the application area.
- Give empty barrels to authorized hazardous waste collector companies.

11 - Safety

Contains Diphenylmethane-4,4'-Diisocyanate. Harmful by inhalation. Irritating to eyes, respiratory system and skin. Do not breathe spray/vapor. Wear suitable protective clothing and gloves. Use only in well-ventilated areas. Pressurized container. Keep away from direct sunlight and do not expose temperatures over 50°C (122°F). Do not pierce or burn, even after use. Keep away from sources of ignition, no smoking. Keep out of the reach of children.

12 - Disclaimer

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.