



PS253

PIPE SEALANT MEDIUM STRENGTH

Akfix PS252 is a medium viscosity and medium strength anaerobic pipe sealant. Thixotropic formulation reduces run-off and migration of the product before assembly.

FIELD OF APPLICATION AND PROPERTIES

- It can be easily applied to threaded joints and removed easily with hand tools.
- With its specialized formulation, PS253 can be used applications where high pressure proof or oil resistance is required.
- The product resists very high temperatures after full curing.

INSTRUCTIONS

- Clean male and female threads before assembly with an absorbent tissue paper to remove any cutting oil.
- Apply the adhesive with a 360 turn to leading threads of the male and female fittings.
- Use an absorbent tissue paper to wipe off excess jointing compound in the direction of the thread.
- Assembly parts and hold on for 24 hours at 22-24°C to ensure full curing of jointing compound.
- For disassembly, use hand tools to remove mating parts. When it is hard to disassemble at room temperature, apply local heat until reaching 250°C and disassemble while hot. Then, remove any residual cured adhesive mechanically and clean parts with a proper solvent, acetone.

Resistance against Environmental Conditions


Environmental resistance of cured adhesive is measured after curing by applying ISO 10964 preloaded assembly test at different conditions.

Test method	:	ISO 10964
Bolt and nut specs.	:	Zinc plated, M10x25
Curing condition and duration	:	22°C, 1 week
Torque test conditions (exception is hot strength test)	:	22°C
Torque type	:	Breakloose Torque (T_{BL})




Hot Strength

Strength is examined at various temperatures. The reference value of '% Full strength on zinc plated' is taken from previous tables corresponding 24 hours curing.



Heat Aging

Strength is examined on specimens that are aged at different temperatures. The reference value of '% Full strength on zinc plated' is taken from previous tables corresponding 24 hours curing.



STORAGE AND SHELF LIFE

Keep product in its original container at 22°C and avoid to contact with direct sunlight. Storage below 5°C and above 30°C can negatively affect product properties.

Material removed from its original container can be contaminated during usage which affects both adhesive performance and storage life. Therefore, do not return contaminated product to the original container.

Shelf life: 36 months at 22°C.



TECHNICAL PROPERTIES

General properties

Main constituent	:	Methacrylate ester
Appearance (uncured)	:	Liquid
Colour	:	Blue
Viscosity	:	Medium and thixotropic
Strength	:	Medium

Physical properties of uncured adhesive

Specific gravity Conditions: 22°C	:	1.03
Flash point Method: ASTM D56-05	:	>93°C
Temperature range	:	-50°C to 150°C
Corrosivity	:	Non-corrosive
Gap filling	:	up to 0.20mm
Viscosity Conditions: 22°C Method: ISO 2555 Apparatus: Brookfield RVT, spindle 3	:	7000 – 15000 cPs (@2.5 rpm)

Typical curing performance of adhesive

Curing time at room conditions

Various type of curing time of adhesive on several substrates are given as follows. Note that results can differ due to distance of bond gap and temperature.

Specimens	:	M10x25 bolt and proper nut
Conditions	:	22°C

Handling time

Material of specimen	Duration
Brass	<30 secs
Steel	2 to 4 mins
Stainless steel	3 to 6 mins
Zinc plated steel	15 to 30 mins
Aluminium	20 to 35 mins

Average functional curing time: 1 to 3 hours


Average full curing time: 8 to 12 hours



Curing speed with different substrates

The curing rate of anaerobic adhesive greatly depends on type of surface material, substrate. The curing rate developed in time is determined by measuring breakaway torque of bolt and nut specimens. Test details and resultant graphs are given below.


Test method	:	ISO 10964
Bolt and nut specs.	:	M10x25
Conditions	:	22°C



Curing speed with different temperatures

Temperature of medium has great impact on curing performance of anaerobic adhesive. The curing rate developed in time is determined by measuring breakaway torque of bolt and nut specimens. Test details and resultant graphs are given below.

Test method	:	ISO 10964
Bolt and nut specs.	:	M10x25
Conditions	:	22°C






Curing speed with different bond gaps

Distance between two surfaces can significantly effect curing rate of adhesive. The curing rate developed in time is determined by measuring shear stress on the one surface of the specimen. Test details and resultant graphs are given below.

Test method	:	ISO 10123
Conditions	:	22°C



Typical properties of cured adhesive

Coefficient of thermal expansion (α) Method: ISO 11359-2	:	$4 \times 10^{-7} \text{ K}^{-1}$
Coefficient of thermal conductivity (k) Method: ISO 8302	:	0.34 W/(m.K)
Specific heat Method: ISO 11357-4	:	0.21 kJ/(kg.K)

Typical cured performance of adhesive

Performance of cured anaerobic adhesive is examined and resultant torque values are given below.

Test method	:	ISO 10964
Conditions	:	22°C
Specimens	:	Different type of nuts and bolts

Unseated assembly cured for 24 hours

Type of specimen	Breakaway Torque (T_{BA})	Prevailing Torque (T_p)
Zinc plated, M10	15 N.m	3 N.m
Stainless steel, M10	12 N.m	2 N.m
Steel, M10	17 N.m	4 N.m



PACKAGING

Product	Volume	Package
Plastic Bottle	15/50ml/250ml	

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.